

PATENT ABSTRACTS OF JAPAN

(11)Publication number : 09-263665

(43)Date of publication of application : 07.10.1997

(51)Int.Cl. C08L 23/14
C08L 23/14
C08K 3/34
//(C08L 23/14
C08L 23:08
C08L 23:18)

(21)Application number : 08-073388 (71)Applicant : IDEMITSU PETROCHEM CO LTD

(22)Date of filing : 28.03.1996 (72)Inventor : TOMOMATSU RYUZO
MIZUNO HIROHIDE
SHIMAZAKI TOSHIFUMI
NARA SHUNEI

(54) PROPYLENE RESIN COMPOSITION AND CAR INTERIOR MATERIAL USING THE SAME

(57)Abstract:

PROBLEM TO BE SOLVED: To provide a propylene resin composition having good appearance, low gloss and excellent shock resistance and car interior materials using the same.

SOLUTION: This propylene resin composition comprises (A) 50-99wt.% of a propylene resin comprising (1) (a) 70-80wt.% of fraction insoluble in p-xylene at 23° C, (b) 30-2wt.% of fraction soluble in p-xylene at 23° C; having (2) (a) the relaxation time (τ) of the component of 0.01-0.35 second and the molecular weight distribution index (PDI) of 1-18, (b) the intrinsic viscosity $[\eta]$ of 2.0-10dl/g and the ethylene unit content of 1-20wt.%; (B) 1-15wt.% of an ethylene-4-18C α -olefin copolymer with a density of 0.850-0.875/cm³ and MI of 0.01-25g/10min and (C) 0-35wt.% of talc. Further, interior parts for cars are produced by injection molding of this resin composition.

LEGAL STATUS

[Date of request for examination] 27.03.2003

[Date of sending the examiner's decision of rejection]

[Kind of final disposal of application other than the examiner's decision of rejection or application converted registration]

[Patent number]

[Date of registration]

[Number of appeal against examiner's
decision of rejection]

[Date of requesting appeal against
examiner's decision of rejection]

[Date of extinction of right]

Copyright (C); 1998,2003 Japan Patent Office